

High-resolution Compton Scattering as a Probe of Fermiology and Electron Correlation Effects

A. Bansil and B. Barbiellini

Physics Department, Northeastern University, Boston, MA 02115, USA

ABSTRACT

Compton scattering is one of the few spectroscopies which directly probes the ground state momentum density in materials. Recent progress in synchrotron light sources has brought a renewed interest in the technique as a tool for investigating fermiology related issues on the one hand, and as a unique window on hitherto inaccessible correlation effects in the electron gas on the other. We provide an overview of some of our recent work on a variety of metals and disordered alloys, including Li, $\text{Li}_{1-x}\text{Mg}_x$, Be, Cu, $\text{Ni}_{75}\text{Cu}_{25}$, $\text{Ni}_{75}\text{Co}_{25}$, Al and Al-Li.

I. INTRODUCTION

Compton scattering is the inelastic scattering of x-rays in the deep inelastic regime (i.e. when the energy and momentum transferred in the scattering process are large). [1–3] It is one of the few spectroscopies which is capable of directly probing the electronic ground state in materials. The measured double-differential cross-section describing the energy and angular distribution of scattered radiation—usually referred to as the Compton profile (CP), can be interpreted as

$$J(p_z) = \int \int n(\mathbf{p}) dp_x dp_y, \quad (1)$$

where $n(\mathbf{p})$ is the ground-state electron momentum density. The theoretical analysis of the Compton spectra in the literature is largely based on the expression of $n(\mathbf{p})$ within the independent particle model:

$$n(\mathbf{p}) = \frac{1}{(2\pi)^3} \sum_{\mathbf{k}\nu} \int |\psi_{\mathbf{k}\nu}(\mathbf{r}) \exp(i\mathbf{p} \cdot \mathbf{r}) d\mathbf{r}|^2, \quad (2)$$

where $\psi_{\mathbf{k}\nu}(\mathbf{r})$ denotes an electron wavefunction in the state $\mathbf{k}$ and band ν , and the summation is over all occupied states. When the right side of Eq. (2) is evaluated using the selfconsistent band theory based electron wavefunctions in the local density approximation (LDA), and the sum is carried out to properly include the Fermi surface (FS) breaks in $n(\mathbf{p})$, one obtains a fairly sophisticated description of the Compton spectrum. Eq. (2) makes it obvious that $n(\mathbf{p})$ and thus the CP contains signatures of both, the shape of the occupied region of the k-space in the first and higher Brillouin zones (BZs), as well as the nature of the electron wavefunctions. Since $n(\mathbf{p})$ in Eq. (1) represents the full many-body ground state

momentum density, a comparison of the measured CP with that obtained via the LDA-band theory framework provides a direct measure of the extent to which the LDA one-particle wavefunctions differ from the true quasiparticle states in the interacting electron gas in the solid.

The Compton technique offers a number of intrinsic advantages over other k-resolved spectroscopies. Being essentially a ground state measurement, the Compton experiment does not require long electron mean free paths as is the case in transport-type experiments such as the dHvA, the latter being limited for this reason to systems with low defect and impurity concentrations. Since no charged particles go in or out of the sample, Compton is not complicated by surface effects present in photoemission or electron scattering experiments, and is thus genuinely a bulk probe. Moreover, because light couples weakly to the electronic system, the disturbance of the electronic states one is trying to measure is relatively smaller in Compton compared to positron annihilation or photoemission-type spectroscopies which involve charged particles.

Historically, the capabilities of the Compton technique have been difficult to realize in practice because only a limited momentum resolution (≈ 0.4 au) was possible with γ -ray sources. However, with the recent availability of second and third generation high-energy, high-intensity synchrotron light sources, and improvements in detector technology it has become possible now to achieve momentum resolution of the order of 0.1 au in wide classes of materials, and of order 0.01 au in low-Z systems. These advances have sparked a renewed interest in the Compton technique as a tool for investigating fermiology related issues on the one hand, and as a unique window on hitherto inaccessible correlation effects in the electron gas on the other. [4,5]

II. AN OVERVIEW OF SELECTED RESULTS

Within space limitations, we give below an overview of some of our recent high-resolution Compton studies in metals and disordered alloys. The list of references is meant to be minimal, but should serve as an entry point into other relevant literature.

1. Li has been the subject of much attention. Ref. [6] may be viewed as marking the beginning of the modern high-resolution Compton studies of solids. Ref. [6] showed that Compton can provide accurate FS dimensions, at least in favorable cases. Furthermore, comparisons between highly accurate first-principles LDA-band-theory based predictions with the corresponding experimental profiles in Li showed clearly that there are systematic discrepancies between theory and experiment which could be attributed to correlation effects on the electron momentum density.
2. Considerable effort has been made to deduce the size of the break Z_F in the momentum density at the Fermi momentum in Li. Z_F is one of the most fundamental parameters which enters in the conventional theory of metals, and it has been investigated using a variety of theoretical approaches for many decades in the homogeneous electron gas. While there is still some uncertainty in analyzing the data, Ref. [7] has estimated a near zero value of Z_F in Li. This is most surprising and very far from theoretical predictions which yield Z_F values ranging from about 0.65 to 0.82 in Li.
3. Several groups have attempted to “reconstruct” the 3D-momentum density in Li from experimental CP’s along several directions. [7–9] In this connection we have computed highly accurate CP’s along various groups of measured directions in Li to serve as a means of testing the accuracy of different reconstruction schemes.
4. $\text{Li}_{100-x}\text{Mg}_x$ disordered alloys have been investigated over the composition range $0 \leq x \leq 40$. [10] The experimental valence CP’s, their second derivatives, and the associated directional anisotropies were compared with the corresponding parameter free KKR-CPA-LDA computations. Discrepancies between measurements and calculations were partly traced back to an inadequate treatment of correlation effects within the LDA. Curiously, the theoretical profiles display a better accord with experiments with increasing Mg concentration, hinting that the behavior of momentum density in

Li may be idiosyncratic and not representative of metals more generally.

5. Be has been another system which has been the subject of several independent studies. The first high-resolution CP’s reported in Ref. [11] showed the essential absence of some theoretically predicted FS signatures in the data. However, this appears to have been due to a lack of adequate statistics in the data of Ref. [11]. Subsequent Compton measurements on Be in Ref. [12] indicated no such serious discrepancies between theory and experiment. Ref. [13] has very recently carried out an extensive new study of Be single crystals using three different incident photon energies. Subtle differences between theoretical and experimental CP’s are pointed out and it is suggested that a better treatment of the correlation effects in the *inhomogeneous* electron gas is needed to develop a satisfactory description of the momentum density in Be.
6. Al has been investigated quite extensively. [14,15] In order to deduce the value of Z_F in Al, the data have been analyzed in terms of a simple model which involves Z_F as a parameter. A good fit with the Compton data is obtained for $Z_F = 0.7$ to 0.8 . [14] Al has also been investigated via Compton experiments where the kinematics of the ejected electron is measured in coincidence with the scattered photon; in principle, such a $(\gamma, e\gamma)$ experiment determines the 3D momentum density directly. The coincidence Compton data on Al indicate a Z_F value of about 0.7. [14] These results suggest that, in sharp contrast to the case of Li, the standard picture of the interacting electron gas is substantially correct in Al.
7. In Cu, high-resolution Compton measurements together with the corresponding highly accurate LDA-based computations along the three principal symmetry directions have been reported recently in Ref. [16]. A reasonable overall picture of the ground state momentum density in Cu is adduced, and the deviations from the band theory predictions are generally found to be consistent with the high-resolution studies of Li and Be.
8. In Ref. [17], we have presented first-principles ferromagnetic electronic structures and spin-resolved Compton profiles along the three high-symmetry directions in Ni, $\text{Ni}_{75}\text{Cu}_{25}$ and $\text{Ni}_{75}\text{Co}_{25}$ disordered alloys. The computations are based on the use of the charge- and spin-selfconsistent KKR-CPA-LDA approach and

involve no free parameters— the lattice constants in all cases were obtained by minimizing the total energy. The majority-spin spectrum of Ni is found to undergo relatively small changes upon alloying with Cu or Co, and indeed the associated CP's in Ni, Ni₇₅Cu₂₅ and Ni₇₅Co₂₅ are very similar. High-resolution magnetic CP experiments are not feasible at the moment, but the theoretical predictions are found to be in reasonable overall accord with the available γ -ray measurements.

9. Finally, we note that very recent experiments on Al-Li alloys with 3% Li seem to indicate that Li-impurities when placed in the Al-matrix may be inducing some very interesting changes in correlations in the electronic system in their vicinity in the alloy. [18] This point is under further investigation.

A few words concerning the theoretical methodology for obtaining highly accurate Compton profiles in metals and alloys are appropriate. Even within the conventional LDA-based band theory framework, highly accurate computations of Compton profiles necessary for analyzing FS signatures are quite demanding. The reason is that the integrand $n(\mathbf{p})$ occurring in Eq. (1) possesses a fairly long range with myriad FS breaks which must be integrated using a fine momentum space mesh. Further, $J(p_z)$ must be evaluated over a fine p_z -mesh extending to quite high p_z values to properly normalize the theoretical profile. We have however developed the methodology to carry out such computations in ordered as well as disordered many atom per unit cell systems, including the possibility of magnetic ordering. [19–22] The relevant Green function formulation for treating momentum density and CP's in disordered alloys is given in Refs. [23,24].

In conclusion, it is clear that high-resolution Compton studies can provide new insights into a variety of issues related to fermiology and correlation effects in metals and alloys. Of particular interest will be problem areas where the conventional k-resolved spectroscopies (dHvA, photoemission and positron annihilation) are difficult to apply due to surface or defect problems, as is the case for example in the oxides generally. Phase transformations and electronic structure and correlation effects under high pressure could be another niche area for Compton scattering since it is difficult to take charged particles in or out of a pressure cell.

ACKNOWLEDGMENTS

It is a pleasure to thank Stanislaw Kaprzyk and Peter Mijnders for important conversations. This work is supported in part by the US Department of Energy contract W-31-109-ENG-38, and benefited from a travel grant from NATO and the allocation of supercomputer time at the NERSC and the North-eastern University Advanced Scientific Computation Center (NU-ASCC).

-
- [1] B. G. Williams, *Compton Scattering* (McGraw-Hill, New York, 1977).
 - [2] M. J. Cooper, Rep. Prog. Phys. **48**, 415(1985).
 - [3] P. E. Mijnders and A. Bansil in *Positron Spectroscopy of Solids*, eds. A. Dupasquier and A. P. Mills, Int. School of Physics 'Enrico Fermi', pp. 257(1995).
 - [4] A. Bansil, Z. Naturforsch. Teil A **48a**,165 (1993).
 - [5] A. Bansil and S. Kaprzyk, Mat. Science Forum **255-257**, 129(1997).
 - [6] Y. Sakurai, Y. Tanaka, A. Bansil, S. Kaprzyk, A. T. Stewart, Y. Nagashima, T. Hyodo, S. Nanao, H. Kawata, and N. Shiotani, Phys. Rev. Lett. **74**, 2252 (1995).
 - [7] W. Schülke, G. Stutz, F. Wohlert, and A. Kaprolat, Phys. Rev. **B54**, 14381(1996).
 - [8] Y. Tanaka, A. Bansil, S. Kaprzyk, P. E. Mijnders, Y. Sakurai, A. T. Stewart and N. Shiotani (preprint).
 - [9] L. Dobrzinski (preprint).
 - [10] G. Stutz, F. Wohlert, A. Kaprolat, W. Schülke, Y. Sakurai, Y. Tanaka, M. Ito, H. Kawata, N. Shiotani, S. Kaprzyk, and A. Bansil, Phys. Rev. **B60**, 7099(1999).
 - [11] K. Hämäläinen, S. Manninen, C.-C. Kao, W. Caliebe, J. B. Hastings, A. Bansil, S. Kaprzyk, and P. M. Platzman, Phys. Rev. **B54**, 5453(1996).
 - [12] M. Itou, Y. Sakurai, T. Ohata, A. Bansil, S. Kaprzyk, Y. Tanaka, H. Kawata, and N. Shiotani, J. Phys. Chem. Sol. **59**, 99(1998).
 - [13] S. Huotari, K. Hamalainen, S. Manninen, S. Kaprzyk, A. Bansil, W. Caliebe, T. Buslaps, V. Honkimäki, and P. Suortti (preprint)
 - [14] P. Suortti, T. Buslaps, V. Honkimäki, C. Metz, A. Shukla, Th. Tschentscher, J. Kwiatkowska, F. Maniowski, A. Bansil, S. Kaprzyk, A. S. Kheifets, D. R. Lun, T. Sattler, J. R. Schneider and F. Bell, J. Phys. Chem. Solids **61**, 397(2000).
 - [15] T. Ohata, M. Itou, I. Matsumoto, S. Kaprzyk, P. E. Mijnders, A. Bansil, Y. Sakurai, H. Kawata and N. Shiotani (preprint).
 - [16] Y. Sakurai, S. Kaprzyk, A. Bansil, Y. Tanaka, G. Stutz, H. Kawata, and N. Shiotani, J. Phys. Chem. Sol. **60**, 905(1999).

- [17] A. Bansil, S. Kaprzyk, A. Andrejczuk, L. Dobrzynski, J. Kwiatkowska, F. Maniawski, and E. Zukowski, Phys. Rev. **B57**, 314(1998).
- [18] I. Matsumoto, J. Kwiatkowska, F. Maniawski, A. Bansil, S. Kaprzyk, M. Itou, H. Kawata and N. Shiotani, J. Phys. Chem. Solids **61**, 375(2000).
- [19] S. Kaprzyk and A. Bansil, Phys. Rev. **B42**, 7358(1990).
- [20] A. Bansil and S. Kaprzyk, Phys. Rev. **B43**, 10335(1991).
- [21] A. Bansil, S. Kaprzyk, and J. Toboła, *Applications of Multiple Scattering Theory in Material Science*, Mat. Res. Soc. Symp. Proc. **253**, 505(1992).
- [22] A. Bansil, S. Kaprzyk, J. Tobola and P. E. Mijnders, Phys. Rev. **B60**, 13396(1999).
- [23] P. E. Mijnders and A. Bansil, Phys. Rev. **13**, 2381 (1976).
- [24] A. Bansil, R.S. Rao, P. E. Mijnders and L. Schwartz, Phys. Rev. **B23**, 3608 (1981).